



LION COPOLYMER

5955 Scenic Highway • Baton Rouge, LA 70805-2044  
800 / 535-9960 • www.lioncopolymer.com

Distribute by Double A Plus Intertrade co.,ltd.  
www.aachemical.com

Trilene® Type	Specific Gravity	Ethylene % <sup>a</sup>	E / P Ratio <sup>b</sup>	Diene %	Molecular Weight		Brookfield Viscosity	
					Mv, Da	Mw, Da	at 60°C	at 100°C
<b>Copolymer</b>								
CP80	0.86	43.0	43 / 57	---	8,000	44,000	500,000	76,000
CP80 Freeflow™	1.00	43.0	43 / 57	---	8,000	44,000	---	---
CP1100	0.85	40.0	40 / 60	---	---	12,000	2,000	100
CP1100 Freeflow™	1.00	40.0	40 / 60	---	---	12,000	---	---
<b>Terpolymers</b>								
<b>DCPD Type</b>								
65	0.86	44.7	50 / 50	10.5	7,000	49,000	1,900,000	177,000
65 C-30		44.7	50 / 50	10.5	7,000	49,000	1,900,000	177,000
65 Freeflow™	1.00	44.7	50 / 50	10.5	7,000	49,000	---	---
<b>ENB Types</b>								
66	0.84	43.0	45 / 55	4.5	8,000	---	640,000	111,000
66 Freeflow™	0.84	43.0	45 / 55	4.5	8,000	---	---	---
67	0.86	40.7	45 / 55	9.5	7,200	42,000	900,000	128,000
67 Freeflow™	0.86	40.7	45 / 55	9.5	7,200	42,000	---	---
76	0.86	72.0	75 / 25	4.0	7,500	---	800,000	102,000
76 Freeflow™	0.86	72.0	75 / 25	4.0	7,500	---	---	---
77	0.86	67.1	75 / 25	10.5	7,500	40,000	800,000	102,000
77 Freeflow™	0.86	67.1	75 / 25	10.5	7,500	40,000	---	---

Trilene Laminate-initial.doc

Notes:

Trilene Freeflow products are 70% active Trilene® adsorbed on precipitated silica carrier.

Trilene 65 C-30 is 30% active Trilene® 65 adsorbed on Burgess KE silane-treated, calcined clay.

<sup>a</sup> Ethylene as a percent of total weight

<sup>b</sup> Weight ratio of ethylene to propylene

**Notice:** All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.